



## LATEST SPECIFICATION OF PURIFIED DRY CHALK (CALCIUM CARBONATE)

TEST PARAMERERS	SPECIFICATIONS
MOISTURE AT 105°	0.60 – 0.80
PURITY AS CaCo3 (%)	98.50
BULK DENSITY, GM/CC	0.86
WHITENESS (%)	99.00
BRIGHTNESS (%)	92,00
LOSS ON IGNITION (AT 900°C (%))	43.80
PARTICLE SIZE (AVERAGE) MICRON	20 -25

[www.sparchem.com](http://www.sparchem.com)

